


Spot Sealer Direct-to-Metal スポット シーラー DTM

FOR PROFESSIONAL USE ONLY

用途


自動車補修の汎用型 1 液速乾エアゾール・ノンサンディングプライマーで、研ぎ出した小範囲な鋼板部分の補修に使用します。



そのまま使用できます



缶を十分に振ってから使用してください
缶の中にある攪拌玉で数分間シェイクしてください。




スプレー距離
約 12 - 18 cm



2 - 3 回シングルコート



使用後はノズル洗浄のため、缶を逆さにスプレーしてください



フラッシュオフタイム:
20°C / 8 - 10 分

最短塗り重ね時間:
20°C / 15 分



塗り重ね可能製品：
シッケンズ プライマーサフェーサー及びトップコート類
但し、プライマーサフェーサーEPは除く。



適切な安全保護具を使用してください
アクゾノーベルではフレッシュエアーマスクの使用を推奨します。

Spot Sealer Direct-to-Metal

スポット シーラー DTM

FOR PROFESSIONAL USE ONLY

用途

自動車補修の汎用型 1 液速乾エアゾールノンサンディングプライマーで、研ぎ出した小範囲な鋼板部分の補修に使用します。

使用できる被塗物

研ぎ出した小範囲の補修に使用してください:

旧塗膜
スチール
銅

亜鉛引き鋼板
アルミニウム

主剤と副剤

エアゾール スポットシーラーDTM

被塗物の前処理



サンディング前に被塗物の不純物をシッケンズ脱脂剤にて除去してください。



最終番手 ドライサンディング P220 - P320



サフェーサー塗装前に被塗物の不純物をシッケンズ脱脂剤にて除去してください。

※ポリエステルパテには M200 (水性洗浄剤) を使用しないでください。

塗装方法




スプレー距離を約 12 - 18 cm に保ち 2-3 回シングルコートしてください。

塗装条件:
温度 15°C - 35°C
湿度 75% 以下



使用後はノズル洗浄のため、缶を逆さにして、2-3 秒スプレーしてください。



各コート間のフラッシュオフタイム (指触乾燥) は 20°C / 8 - 10 分です。

Spot Sealer Direct-to-Metal


スポット シーラー DTM

FOR PROFESSIONAL USE ONLY

膜厚

推奨する方法にて塗装した場合： 20 - 30 μm

塗り重ね時間



20°C / 15 分以上 48 時間以内に下記の製品を塗装してください。

塗装後 20°C / 48 時間以上放置した場合にはサフェーサーやトップコート塗装前に必ずドライサンディング P500 又はウェットサンディング P1000 にてサンディングしてください。

塗り重ね可能製品



すべてのシッケンズプライマーサフェーサー類及びトップコート類
但し、プライマーサフェーサーEP は除く。

VOC 含有量

716g / L (理論上での希釈済み塗料)

製品の保管

製品の貯蔵安定期間は、20°Cで未開封の場合を基準としています。

※貯蔵安定期間については TDS S9.01.02 を参照してください。

アクゾノーベル株式会社 自動車補修塗料事業部
東京都国立市泉 4 丁目 8 - 7
Tel :042 - 843 - 0081

FOR PROFESSIONAL USE ONLY

IMPORTANT NOTE The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to Akzo Nobel.

Head Office

AkzoNobel Car Refinishes B.V., PO Box 3 2170 BA Sassenheim, The Netherlands. www.sikkenscr.com