


Polystop LP

FOR PROFESSIONAL USE ONLY

Description			
Two-pack polyester bodyfiller designed to fill dents and surface irregularities on large surfaces. As a result of its fine texture, Polystop LP is eminently suitable to be applied as a finishing filler over coarser types of polyester fillers.			
	100	Polystop LP	
	1-3	AkzoNobel Putty Hardener	
	3% Hardener	2% Hardener	1% Hardener
	7 minutes at 20°C	11 minutes at 20°C	20 minutes at 20°C
	3% Hardener: 30 minutes at 20°C		
	2% Hardener: 40 minutes at 20°C		
	1% Hardener: 50 minutes at 20°C		
	Final sanding step for bodyfiller P180 - P220		
	Final sanding step for eatheredge P320 - P400		
	Recoatable with all Sikkens solventborne preparatory products*		
	• With the exception of water containing products		
	Use suitable respiratory protection		
	Akzo Nobel Car Refinishes recommends the use of a fresh air supply respirator.		

Read complete TDS for detailed product information

Polystop LP

FOR PROFESSIONAL USE ONLY

Description

Two-pack polyester bodyfiller designed to fill dents and surface irregularities on large surfaces. As a result of its fine texture, Polystop LP is eminently suitable to be applied as a finishing filler over coarser types of polyester fillers.

Preparation process



Remove contamination using an appropriate cleaner



Final step P180 - P220

For detailed surface preparation see TDS S8.06.02



Remove contamination using an appropriate cleaner

Suitable substrates

Steel
Primer Surfacer EP II (maximum 25 µm)
Polyester laminates


Products and additives

Polystop LP
AkzoNobel Putty Hardener

Basic raw materials

Polystop LP: Polyester resins
Hardener: Peroxide

Mixing



100 parts Polystop LP
1-3 parts AkzoNobel Putty Hardener

Mix to a homogeneous, uniform colored mass

*Avoid air entrapment
Preferably mix on a scale*

Pot-life

7 minutes at 20°C when mixed with 3% putty hardener
11 minutes at 20°C when mixed with 2% putty hardener
20 minutes at 20°C when mixed with 1% putty hardener

Polystop LP

FOR PROFESSIONAL USE ONLY

Application



Apply Polystop LP to bare substrate at a 60° angle.
Avoid ridges of bodyfiller around the perimeter of the repair.

- Do **not** apply Polystop LP to existing finishes or washprimer.
- Application temperature range between 15°C-35°C

Drying



Ready to sand after
3% Hardener: 30 minutes at 20°C or 20 minutes at 40°C
2% Hardener: 40 minutes at 20°C or 30 minutes at 40°C
1% Hardener: 50 minutes at 20°C or 40 minutes at 40°C



Ready to sand after 5 minutes at low power at a 50-70 cm distance.
The panel temperature should not exceed 90°C.
For additional information, see TDS S9.01.01

Sanding process



P80 - P120 - P220
Use a guide coat at each sanding step.



P220 - P320 (P400 for a spot repair).
Make sure to remove coarse sanding scratches from the feather edge area



Remove contamination using an appropriate cleaner
Do not use a waterborne degreaser

Recoatable with

All Sikkens solventborne preparatory products

Note: Do not recoat with Autosurfacer WB

Cleaning of equipment

Clean equipment immediately after use with Sikkens Solvent or a solvent borne guncleaner.

VOC

2004/42/II(b)(250)120

The EU limit value for this product (product category: IIB. b) in ready to use form is max. 250 g/liter of VOC.
The VOC content of this product in ready to use form is max. 120 g/liter.

Product storage

Product shelf-life is determined when products are stored unopened at 20°C
Avoid extreme temperature fluctuation.

Polystop LP

FOR PROFESSIONAL USE ONLY

- Product shelf life data see TDS S9.01.02

Akzo Nobel Car Refinish bv.
Adress: Rijkssstraatweg 31, PO Box 3, 2170 BA Sassenheim
Tel: +31(0)71308-6944

FOR PROFESSIONAL USE WITH SUITABLE HS&E EQUIPMENT

IMPORTANT NOTE The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to Akzo Nobel.

Head Office

Akzo Nobel Car Refinishes B.V., PO Box 3 2170 BA Sassenheim, The Netherlands. www.sikkenscr.com

Polystop LP

FOR PROFESSIONAL USE ONLY

