

AkzoNobel

AkzoNobel has a passion for paint. We're experts in the proud craft of making paints and coatings, setting the standard in color and protection since 1792. Our world class portfolio of brands – including Dulux, International, Sikkens and Interpon – is trusted by customers around the globe. Headquartered in the Netherlands, we operate in over 80 countries and employ around 35,000 talented people who are passionate about delivering the high performance products and services our customers expect. For more information please visit www.akzonobel.com

© 2019 AkzoNobel N.V. All rights reserved.

DYNACOAT

CLEAR MATT

**FOR COMPLETE
CONFIDENCE
IN REPLICATING
REDUCED-GLOSS
OEM FINISHES**



CLEAR MATT

DYNACOAT CLEAR MATT IS PART OF A COMPLETE VEHICLE REFINISHING SOLUTION THAT GIVES YOU OPTIMAL RESULTS AND HONEST, TRUSTED VALUE. THIS VOC-COMPLIANT, TWO-COMPONENT MATTING CLEARCOAT IS DESIGNED TO REPLICATE REDUCED-GLOSS OEM FINISHES PRECISELY IN ALL APPLICATIONS AND CONDITIONS. ITS APPLICATION IS EASY, VERSATILE AND FAST.

GLOSS LEVEL PRECISION

For a matt finish, Clear Matt is mixed purely with Dynacoat Flexi Hardeners, Hardener 420 and universal thinners. For eggshell or semi-gloss finishes, Dynacoat clearcoats can be added to the mix.

Use Clear 6000 HS Antiscratch or Clear 9000, according to the table below, to achieve a perfect match in gloss level.

USING CLEAR 6000 HS ANTISCRATCH (MIXING RATIO 2:1+10% WITH DYNACOAT FLEXI HARDENERS)

Matt Finish 100% Dyncoat Clear Matt	10-20 G.U
Eggshell Finish 4 volumes- Dynacoat Matt 1 Volumes- Dynacoat Clear 6000 HS Antiscratch	30-40 G.U
Semi- gloss finish 3 volumes - Dynacoat Clear Matt 2 volumes - Dynacoat Clear 6000 HS Antiscratch	50-70 G.U
1 volumes - Dynacoat Clear Matt	70- 80 G.U

USING CLEAR 9000 (MIXING RATIO 2:1:10% WITH DYNACOAT HARDENER 420)

Matt Finish 100% Dyncoat Clear Matt	15-25 G.U
Eggshell Finish 4 volumes- Dynacoat Matt 1 Volumes- Dynacoat Clear 9000	35-45 G.U
Semi- gloss finish 3 volumes - Dynacoat Clear Matt 2 volumes - Dynacoat Clear 9000	60-75 G.U


FOR COMPLETE CONFIDENCE IN REPLICATING REDUCED-GLOSS OEM FINISHES

SPEED AND FLEXIBILITY

A choice of hardeners and thinners allows simple adjustment to different job sizes and environmental conditions.

Clear Matt is easy, quick and efficient to apply – in just two coats with a short flash-off – to create smooth, high-quality finishes, including attractive silky gloss effects.


FEATURES	BENEFITS
Intermixable with Clear 6000 HS Antiscratch or Clear 9000	<ul style="list-style-type: none"> ▪ Accurate adjustment and control of gloss level ▪ Precise matching of OEM finish, including silky gloss effects
Use of existing family hardeners and thinners	<ul style="list-style-type: none"> ▪ Wide application window and flexibility for different conditions and repair sizes ▪ Reduced complexity and stock needs
Easy application	<ul style="list-style-type: none"> ▪ No additional training needed ▪ Painter confidence ▪ Less risk of error ▪ Smooth finish
Two-coat application and short flash-off time (5-10 minutes)	<ul style="list-style-type: none"> ▪ Time and material savings
VOC compliance	<ul style="list-style-type: none"> ▪ Healthy environment ▪ Meets EU VOC directive requirements



2 : 1 : 10%




D1



2 x 1 coat



1.2-1.4 mm
1.7-2.2 bar



Between coats:
5-10 mins
Before curing:
10-15 mins



Dynacoat Flexi
Hardener
6-7 hrs @ 20°C
20-25 min
@ 60°C

