

QUICK DRY WOODSTAIN

Dulux Trade Quick Dry Woodstain is a high performance water-based product formulated using unique **AkzoNobel** technology. It produces a highly flexible medium build satin finish which provides excellent resistance to peeling, flaking and blistering. Quick drying, it protects exterior wood for up to 10 years if used in accordance with instructions.

KEY BENEFITS

- 10 Year **Weathershield** Protection
- Doors, Windows & Other Joinery
- Water-Based

PRODUCT INFORMATION

Typical Use

Suitable for hardwoods and softwoods.

Pack Size

1L, 2.5L and 5L.

Colour Range

See appropriate **Dulux Trade** colour literature or visit duluxtrade.co.uk.

Film Thickness

Film thickness will be dependent upon the coverage achieved. A nominal figure at 20m² per litre will give a wet film thickness of 50 microns.

Composition (nominal)

Pigment: Special Transparent Iron Oxide Micro Pigments and Organic Pigments.

Binder: Adhesion Promoted Acrylic Copolymer Emulsion with a Fungicide, for the purpose of protecting the film.

Solvent: Water.

Volume Solids

35% (nominal) for semi-translucent colours.

SURFACE PREPARATION

To get the best results, ensure surfaces to be stained are sound, clean and dry. Remove all loose and defective coatings and previous paintwork, if necessary stripping back to bare wood. Where the surface has been previously painted, it will be necessary to strip back to bare wood. Special

precautions should be taken during surface preparation of pre-1960s paint surfaces over wood and metal as they may contain harmful lead.

Remove and treat any mould, algae, lichen or moss with **Weathershield Fungicidal Wash***. Remove defective glazing material, clean the rebates and any loose or open joints. Replace any rotten wood and troublesome knots with new preservative treated timber.

Thoroughly rub down all surfaces in the direction of the grain to remove any grey, weathered wood and surface sheen from remaining coatings, and then dust off (refer to COSHH Assessment).

Fill any surface defects, open joints, etc. and replace any missing glazing material. Do not use linseed oil putty for glazing (or making good) with natural wood finishes, use external beads set in an appropriate non-setting mastic or a special glazing compound.

SYSTEMS INFORMATION

Prime all bare wood with 2 coats of Dulux Trade Weathershield Preservative Primer including any new or bare replacement beading. Apply second coat as soon as the first coat has soaked in. This typically takes 2-6 hours. Do not allow first coat to fully dry before applying the second coat as this will reduce penetration into the wood and prolong total drying time. Allow 16 hours for second coat to dry then mix the normal finishing process with 2 coats of **Dulux Trade Quick Dry Woodstain**.

STIR THOROUGHLY BEFORE USE

New joinery is often factory primed using a stain basecoat (also called a dual-purpose primer). These materials quickly erode when left exposed and may need to be re-primed.

When treating timber that has been pressure impregnated with preservative ensure that the surface is completely dry

The use of silicone sealants can cause 'cissing' of this product.

QUICK DRY WOODSTAIN

Do not use on resinous wood or woodwork with a history of blistering. The maximum benefits of this system will only be realised when used as directed above on good quality timber that conforms to BS EN 942: 1996 (or as amended), in conjunction with good component design.

For best colour consistency, purchase sufficient tinted paint for each job including touch-in at one time from the same source.

APPLICATION METHOD

Brush only. Do not spray.

As with other water-based paints, do not use in temperatures below 8°C (as recommended by British Standard BS 6150).

Practical Coverage

A guide to the practical coverage which can be achieved under normal conditions is up to 20m² per litre, depending on the porosity of the wood.

Spray Recommendations

This product is not suitable for spray application.

Drying Times

Single coat at standard thickness:

Touch Dry: Within 1 hour but dependent on temperature and humidity.

Recoat: 2 hours under normal drying conditions.

Responsible Cleaning

Cleaning After Final Use: Cleaning your brushes and rollers immediately after their final use ensures they can be reused for multiple projects, saving you money and reducing waste.

Cleaning:

1. **Remove Excess Paint:** Scrape off excess paint into container for future projects.

2. **Clean with Warm, Soapy Water:** Use warm, soapy water in a sealed container, such as a bucket or empty tub, to clean your brushes and rollers.
3. **Rinse Thoroughly:** Ensure all soap and paint residues are completely rinsed out into container.
4. **Dry Naturally:** Allow brushes and rollers to dry naturally and store them in a dry, dust-free place.
5. **Allowing solids to settle:** Allow the paint solids to settle at the bottom of the container. Once settled, pour the clear water into another container for reuse or disposal.
6. **Responsible Disposal:** Let the remaining paint solids dry out completely and dispose of them as solid waste.

Do not flush paint down the drain, including when cleaning painting tools

For professional cleaning tips, check out this video created in partnership with the British Coatings Federation and Dulux Connect contractor Bagnall's: <https://coatings.org.uk/general/custom.asp?page=HowToCleanPaintbrushes>

When this paint container is empty please ask your stockist about recycling. If you have leftover paint, please dispose of it responsibly and consider donating it to **Community RePaint**. Find out more at duluxtrade.co.uk/sustainability

Transportation & Storage

Do not use or store in extremes of temperature and protect from frost. To prevent spillage, please store and transport upright.

VOC

EU limit value for this product (cat.: A/e): 130g/l (2010). This product contains max. 65g/l VOC. VOC content: Low (0.30-7.99%).

FURTHER SUPPORT

If you need further support, please contact the **AkzoNobel** Technical Advice Centre on [0333 222 70 70](tel:03332227070).

***Weathershield** Multi-Surface Fungicidal Wash contains: Benzalkonium Chloride.

***Always read full Health, Safety & Environmental Information on can before use.**

Safety datasheet is available free on request by telephoning the **AkzoNobel** Technical Advice Centre or by visiting duluxtrade.co.uk



Issued 08/25

615

QUICK DRY WOODSTAIN

AkzoNobel, the AkzoNobel logo, the Flourish logo, Dulux Trade, Weathershield, and Community RePaint are trademarks of the AkzoNobel group. © AkzoNobel 2023.