

Adhesion Primers 01/05/2020 L2.04.04 UK & Ireland

DESCRIPTION

Lesonal UV Filler is a one-component UV curable filler suitable for small repairs. The filler only needs 5 minutes of curing by UV light and offers customers the opportunity to drastically reduce their preparation process time.



Shake thoroughly before use

Application distance



Approx. 10-20 cm

Application



2-3 x 1 coat

Flash-off



Between coats 2 minutes at 20°C

Before curing 5 minutes at 20°C



After use, invert aerosol to clear nozzle

Drying



400W HID lamp UV LED 5 minutes 5 minutes Ensure suitable UV protection is observed

Sanding



Final sanding step: P500

Protection



Use suitable respiratory protection

Akzo Nobel Car Refinishes recommends the use of fresh air supply respirator

Read complete technical data sheet for detailed product information



Adhesion Primers	01/05/2020	L2.04.04 UK & Ireland

DESCRIPTION

Lesonal UV Filler is a one-component UV curable filler suitable for small repairs. The filler only needs 5 minutes of curing by UV light and offers customers the opportunity to drastically reduce their preparation process time.

PRODUCT AND ADDITIVES

Product UV Filler

Chemical Basis UV Filler Acrylic resins

METHOD OF USE

Substrates Original finishes, including thermoplastic acrylics

Steel

Zinc coated steel
Aluminium

1K Multi Plastic Pr

1K Multi Plastic Primer Polyester Body Filler

For systems which should meet the highest standards, pre-treat the metal substrate with

AkzoNobel AutoPrep Pre-treatment Wipes

Substrate preparation Original finishes: Sand with P180-P280 grit dry

Steel: Sand with P180-P280 grit dry

Polyester Body Filler: Sand with P180-P280 grit dry

Mixing ratio



RFU UV Filler



UV Filler must be shaken thoroughly for 30 seconds before use



Adhesion Primers 01/05/2020 L2.04.04 UK & Ireland

APPLICATION TECHNIQUE

Application

Apply two or three single coats.





After use, invert aerosol to clear nozzle



Position the HID lamp or LED approx..40 cm from the surface, ensuring the repair area is covered by the UV foot print

	Time to full intensity	Drying time
400W HID lamp	3 minutes	5 minutes
UV LED	1 minute	5 minutes

Use the UV unit according recommendation

Tesla Cure R100 UV LED Handlamp

Repair size	Flash off with UV	Curing time
Small spot	3-8 sec	30 sec
Medium spot	3-8 sec	1 min
Half panel	3-8 sec	2 min

Personal protection equipment

Basecoat WB GT

When curing UV Filler, it is necessary to use suitable UV protection equipment which covers all skin areas on hand, arm and face. Wear long sleeves, gloves and cover the face with suitable full-face shield.

Layer thickness	80 – 100 microns			
Sandpaper grades	Dry sanding :	Initial sanding P320	Final sanding P400-P500	
Recoatability	Topcoat HS 420			

3/4 AkzoNobel



Adhesion Primers	01/05/2020	L2.04.04 UK & Ireland
Product storage	Avoid extreme temperature fluctuation and high humidity levels	
Shelf life	1 year at 20°C	
VOC	2004/42/IIB(e)(840)400 The EU limit value for this product (product category : IIB.e) in ready to use g/I VOC. The VOC content of this product in ready to use form is max. 400 g/litre.	form is max. 840

Akzo Nobel Coatings LTD Address: Unit 2B, Didcot Park

Churchward, Southmead Industrial Estate

Didcot, Oxfordshire, OX11 7HB **Tel:** 00 44 (0)1235 862226

FOR PROFESSIONAL USE ONLY

IMPORTANT NOTE: The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfil the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give, or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel.

Head Office

Akzo Nobel Car Refinishes B.V., PO Box 3 2170 BA Sassenheim, The Netherlands. www.Lesonal.com